



3M™ Controltac™ Graphic Film

- IJ180-10
- With Comply™ Adhesive IJ180C-10
- With Comply™ v3 Adhesive IJ180Cv3-10

For the most current 3M Technical Information available to successfully use this product, please view this Bulletin electronically and click on the blue underlined links to view the relevant documents.

For Solvent, UV and Latex Inkjet Printing

1. Product Description

A. Product Features

- 2-mil white, vinyl film with a luster finish
- Excellent hiding power
- Pressure-activated adhesive for easy sliding, tacking, snap up and repositioning
- Flexible; conforms to compound curves, corrugations and rivets
 - Many finished graphic constructions can be stretched up to 130% (i.e., a 10 inch [25 cm] piece of film can stretch to 15 inches [39 cm]) without primer or relief cuts and maintain lift resistance; see details and exceptions in Section 8 on page 12.
- Films IJ180C-10 and IJ180Cv3-10 have Comply™ Adhesive air release channels for fast, easy, bubble-free installations
- Film IJ180Cv3-10 air release channels are non-visible and have improved air release
- Removable with heat and/or chemicals

B. Recommended Types of Graphics and End Uses

When constructed and used as described in this Bulletin, these types of graphics and end uses may be warranted by the 3M™ MCS™ Warranty or the 3M Performance Guarantee. Please read the entire Bulletin for details.

- Indoor and outdoor graphics and signs, including point-of-purchase and displays
- Commercial vehicles, straight trucks, semi-trucks and semi-trailers; emblems or striping
- Bus graphics
- Personal vehicle graphics and wraps
- Non-vertical and horizontal vehicle wraps when protected with 3M overlaminates 8528, 8548G or 8549L
- Watercraft graphics (above the static water line only)
- Small format original equipment manufacturer's (OEM) decorative and identification graphics, cautionary and safety labeling

C. Performance Overview

3M tests the performance of both individual products and finished graphic constructions. This table shows the best performance expected from this product without a Warranty Period and with a Warranty Period.

For detailed graphic construction and application options along with specific Warranty Periods, please see the Warranty Information, Section 5 on page 5.

Expected Performance Life. This is the estimated period of time the product should perform satisfactorily.	
Unprinted film with no graphic protection, applied to a flat vertical outdoor surface.	10 years Unwarranted Period
3M™ MCS™ Warranty. This is the maximum period of time 3M will warrant the finished graphic performance.	
Printed film with the best 3M ink and graphic protection option, applied to a flat, vertical, vehicle type surface.	7 years Warranty Period
3M Performance Guarantee. This is the maximum period of time 3M will warrant the performance of the 3M materials used.	
Printed film with the best ink and graphic protection option, applied to a flat, vertical, vehicle surface.	4 years Warranty Period

D. Limitations of End Uses

This 3M product is not designed or recommended for the following uses. Please contact us to discuss other options.

(1) Unsuitable End Uses for This Film

- Do not use for graphics applied to:
 - stainless steel (consider [3M™ Controltac™ Graphic Film IJ181](#) instead).
 - non-3M films (see Removal Warranty).
 - watercraft when the graphic is below the static water line.
 - watercraft graphics that are not edge sealed.
 - painted substrates with poor paint to substrate, or paint-to-paint bond.
 - substrate surfaces that are not clean and smooth (little or no variation in texture).
- **For film with Comply v3 adhesive only:** Do not use prespacing tape for cut and weeded applications where the tape must adhere to the exposed liner.
- Do not use the film without graphic protection for:
 - printed vehicle graphics.
 - watercraft graphics.
 - exposed to abrasive conditions, harsh cleaners or chemicals.
 - horizontally-exposed outdoor applications.
- Do not use the film for graphics that require removal from:
 - applications with poor paint-to-substrate adhesion.
 - existing graphics that must remain intact; damage may occur during removal of film.
 - watercraft.
 - outdoor, horizontal applications (except graphics using overlaminates 8528, 8548G, or 8549L as described in this Bulletin).
- Do not use for graphics subjected to gasoline vapors or spills, including those at or on gas pumps, automobile fuel-tank ports, watercraft or top-feeding, petroleum tankers

(2) Wall Graphics

Two-mil cast films are typically the best choice for indoor smooth surface wall graphics. However, the user is responsible for determining the product's suitability, including adhesion and, if required, removal characteristics. Due to the wide variability of smooth indoor walls, neither finished graphics nor removal is warranted, even for removable or changeable films. [3M Instruction Bulletin 5.37](#) provides comprehensive information for the most successful wall graphics film selection and application.

(3) Important Information About Bus Applications

Film used on buses must not be applied so as to restrict the safe use of emergency window exits. See the most current version of [3M Instruction Bulletin 5.4](#) for details.

2. Compatible Products

The following products are approved by 3M for use with the base film covered in this Bulletin and used for the creation of a graphic that may be eligible for the 3M™ MCS™ Warranty or 3M Performance Guarantee. Click on the blue underlined text to view the Product Bulletin for that product.

A. Inkjet Inks and Printers Eligible for 3M™ MCS™ Warranty

(1) Solvent Inkjet Inks

Ink Series

- [3M™ Piezo Inkjet Ink Series 1500v2](#)
- [3M™ Piezo Inkjet Ink Series 4400](#)
- [3M™ Piezo Inkjet Ink Series 4800](#)
- [SIIT GX 3M Ink Series](#)
- [SIIT SX 3M Ink Series](#)

Printer

- EFI™ VUTEK® 150, 2360/3360, 3300/5300 & 3000/5000 Printers
- HP XLJet 1200 and 1500 Printers
- HP Scitex TJ8300 & TJ8350 Industrial Presses
- Seiko I Infotech ColorPainter™ H Series H-74s, H2-74s, H-104s, H2-104s, W-54s & W-64s Printers
- Seiko I Infotech ColorPainter™ M-64s Printer

(2) Latex Inkjet Inks

- [HP 3M LX600 Specialty Latex Ink](#)
- [HP LX610 Latex Ink](#)
a 3M™ MCS™ Warranty Component
- [HP 792 Latex Ink](#)
a 3M™ MCS™ Warranty Component
- [HP 881 Latex Ink](#)
a 3M™ MCS™ Warranty Component
- HP 831 Latex Ink
a 3M™ MCS™ Warranty Component
- HP Designjet L65500; Scitex LX600, LX800, LX820 & LX850; Latex 820 & 850 Printers
- HP Designjet L65500, Scitex LX600, LX800, LX820 & LX850; Latex 820 & 850 Printers
- HP Designjet L26100, L26500 & L28500 Latex 210, 260 & 280 Printers
- HP Latex 3000 Printer
- HP Latex 360 Printer

(3) UV Inkjet Inks and Printers

- [3M™ Piezo Inkjet Ink Series 2200UV](#)
- [3M™ Piezo Inkjet Ink Series 2800UV](#)
- [EFI™ VUTEK® GS 3M™ Premium UV Inks](#)
- [EFI™ VUTEK® GSr 3M™ Premium UV Inks](#)
- [EFI™ VUTEK® GSLXr 3M Superflex UV Ink](#)
(excludes White Ink)
- [EFI™ R3225 3M™ UV Ink](#)
- [Mimaki LF-200 Ink Series](#)
Manufactured by 3M
- [Mimaki UV Ink LUS-200](#)
Manufactured by 3M
- EFI™ VUTEK® PV200 Printer
- EFI™ VUTEK® QS2000, QS3200, QS3220 and QS220 Printers
- EFI™ VUTEK® GS2000, GS3200 & GS3250 Printers, including GS Pro Series
- EFI™ VUTEK® GS5000r & GS3250r Printers
- EFI™ VUTEK® GS3250LXr and GS5500LXr Pro Printers
- EFI™ R3225 UV Roll-to-Roll Printer
- Mimaki UJV-160, JFX-1631 & 1615R Printers
- Mimaki UJV500-160 Printer

B. OEM Inkjet Inks and Printers for the 3M Performance Guarantee

- For the most current information, please click here: [3M Performance Guarantee Matrix](#).

C. Graphic Protection

- [3M™ Scotchcal™ Gloss Overlaminates 8518](#)
- [3M™ Scotchcal™ Luster Overlaminates 8519](#)
- [3M™ Scotchcal™ Matte Overlaminates 8520](#)
- [3M™ Scotchcal™ Gloss Overlaminates 8528](#) *with horizontal vehicle warranty*
- [3M™ Envision™ Gloss Wrap Overlaminates 8548G](#) *with horizontal vehicle warranty*
- [3M™ Scotchcal™ Luster Wrap Overlaminates 8549L](#) *with horizontal vehicle warranty*
- [3M™ Scotchcal™ Luster Overlaminates 8908](#)
- [3M™ Scotchcal™ Matte Overlaminates 8909](#)
- [3M™ Scotchcal™ Ultra Matte Overlaminates 8915](#)
- [3M™ Screen Print Gloss 1920DR](#)
- [3M™ Screen Print UV Gloss Clear 9740i](#)
- [3M™ Piezo Inkjet Protective Clear 8530](#)

D. Other Products

- [3M™ Premasking Tape SCPM-3](#)
- [3M™ Premasking Tape SCPM-44X](#)
- [3M™ Prespacing Tape SCPS-2](#)
- [3M™ Prespacing Tape SCPS-55](#) *for films with Comply™ Adhesive*
- [3M™ Prespacing Tape SCPS-53X](#)
- [3M™ Edge Sealer 3950](#)
- [3M™ Edge Sealer Tape 8914](#)
- [3M™ VentureShield™ Matte Finish Film 7710-LD](#)
- [Scotchgard™ Paint Protection Film SGH6](#)

3. Characteristics

These are typical values for unprocessed product. Processing may change the values. Contact your 3M representative for a custom specification.

A. Physical Characteristics

Characteristic	Value												
Material	Cast vinyl												
Film color	White, opaque												
Thickness	Without adhesive: 2 mil (0.05 mm) With adhesive: 3-4 mil (0.08-0.10 mm)												
Adhesive	Film IJ180: Pressure-activated (slide, tack, snap up, reposition) Films IJ180C, IJ180Cv3 (all versions): Pressure-activated (slide, tack, snap up, reposition) with air release channels												
Adhesive color	Gray												
Liner	Polyethylene-coated paper												
Adhesion, Typical 24 hours after application	<table border="0"> <tr> <td>ABS</td> <td>4-5 pounds/inch (0.72-0.89 kg/cm)</td> </tr> <tr> <td>Acrylic enamel</td> <td>3-4 pounds/inch (0.54-0.72 kg/cm)</td> </tr> <tr> <td>Aluminum, anodized</td> <td>7-8 pounds/inch (1.26-1.43 kg/cm)</td> </tr> <tr> <td>Aluminum, etched</td> <td>5-6 pounds/inch (0.89-1.08 kg/cm)</td> </tr> <tr> <td>Chrome</td> <td>4-5 pounds/inch (0.72-0.89 kg/cm)</td> </tr> <tr> <td>Fruehauf pre-painted panels</td> <td>3-5 pounds/inch (0.54-0.89 kg/cm)</td> </tr> </table>	ABS	4-5 pounds/inch (0.72-0.89 kg/cm)	Acrylic enamel	3-4 pounds/inch (0.54-0.72 kg/cm)	Aluminum, anodized	7-8 pounds/inch (1.26-1.43 kg/cm)	Aluminum, etched	5-6 pounds/inch (0.89-1.08 kg/cm)	Chrome	4-5 pounds/inch (0.72-0.89 kg/cm)	Fruehauf pre-painted panels	3-5 pounds/inch (0.54-0.89 kg/cm)
ABS	4-5 pounds/inch (0.72-0.89 kg/cm)												
Acrylic enamel	3-4 pounds/inch (0.54-0.72 kg/cm)												
Aluminum, anodized	7-8 pounds/inch (1.26-1.43 kg/cm)												
Aluminum, etched	5-6 pounds/inch (0.89-1.08 kg/cm)												
Chrome	4-5 pounds/inch (0.72-0.89 kg/cm)												
Fruehauf pre-painted panels	3-5 pounds/inch (0.54-0.89 kg/cm)												
Tensile strength	5 pounds/inch at 73°F (0.9 kg/cm at 23°C)												
Chemical resistance	<ul style="list-style-type: none"> Resists mild alkalis, mild acids, and salt Excellent resistance to water (<i>does not include immersion</i>) Resists occasional fuel spills 												
Flammability	ASTM E84 reports: IJ180 , IJ180C and IJ180Cv3 or go to the On-line Product Catalog at 3Mgraphics.com All other test reports: call 1-800-328-3908												


B. Application Characteristics

Characteristic	Value
Finished graphic application recommendation	<p>Surface type: Flat, with and without rivets, simple curves, compound curves, and corrugations</p> <p>Substrate type: ABS resins, aluminum, chrome, glass, fiberglass reinforced plastics, paint (check adhesion to powder-coated or water-based paints), fiberglass with gel coat</p> <p>Application method: Dry</p> <p>Application temperature: <i>air and substrate</i></p> <ul style="list-style-type: none"> Flat without rivets: 40°-100°F (4°-38°C) Curves or corrugations with rivets: 50°-100°F (10°-38°C) Compound curves and/or watercraft: 60°-90°F (16°-32°C)
Applied shrinkage	0.015 inches (0.4 mm)
Temperature range after application	-65° to +225°F (-60° to +107°C)
Graphic removal	Removable with heat and/or chemicals from most substrates within the Warranty Period at 50°F (10°C) minimum (air and substrate)

4. Definitions


A. Exposure Types

U.S. Vertical Exposure



The face of the graphic is +/- 10° from vertical.

U.S. Non-vertical Exposure



The face of the graphic is greater than 10° from vertical and greater than 5° from horizontal. This includes non-vertical surfaces of vehicle wraps or fleet truck and trailer graphics.

U.S. Horizontal Exposure



The face of the graphic is +/- 5° from horizontal.

U.S. Desert Southwest Exposure

Any outdoor graphic exposed to solar energy more than half of the daylight hours in Arizona, New Mexico and the desert areas of California, Nevada, Utah and Texas is subject to reduced warranties. [Click here](#) for a detailed map.

B. Graphic Construction

The products used to make a graphic, which may include film and/or flexible substrate, graphic protection, ink, printer and application tape.

C. Graphic Protection

Overlaminates films or clear coats used to protect the graphic and/or change gloss.

D. Graphic Types

As identified in Product Warranty Matrices

Indoor Signs

Stationary graphics applied indoors and *not* exposed to the elements.

Outdoor Signs

Stationary graphics applied outdoors and exposed to the elements.

OEM

Labels and decorative graphics produced for and used by original equipment manufacturers. May also be called decals.

Vehicle Types

Vehicle. Buses, vans, passenger vehicles, delivery trucks, pickup trucks, enclosed trailers.

Straight Trucks, Semi-Tractors and Semi-Trailers. Straight trucks, semi-tractors and semi-trailers used for commercial business purposes. Excludes air shields.

Recreational Vehicle (RV). Vehicles used for personal pleasure, such as campers, motor homes and trailers, that are not used in connection with any commercial or business enterprise.

Watercraft. Boats intended for personal pleasure such as runabouts and speedboats having aluminum and/or smooth fiberglass/gel coat bodies, including boats used in fishing tournaments and off-shore racing boats, but not 1 to 3 person personal watercraft or other boats used in connection with commercial or business enterprise. 3M specifically excludes all other recreational vehicles from this definition.

Rail. Rail cars and lead cars of trains, light rail and subways, but not locomotives or engines.

5. Warranty Information

A. Warranty Coverage Overview

The Warranty coverage for each graphic is based on the user(s) both reading and following all applicable and current 3M Product and Instruction Bulletins. 3M will honor eligible graphics for the Warranty Period stated in the base film's Product Bulletin that is current when the film was purchased. The Warranty Period may be reduced and stipulations may apply for certain constructions and applications, as covered in this Bulletin.

The following is made in lieu of all other express or implied warranties, including any implied warranty of merchantability or fitness for a particular purpose or implied warranty arising out of a course of dealing, custom or usage of trade.

B. 3M Basic Product Warranty

This product is warranted to be free of defects in materials and manufacture at the time of shipment and to meet the specifications stated in this Product Bulletin and as further set forth in the [3M Graphics Warranties Brochure](#).

C. Limited Remedy

3M will replace or refund the price of any 3M materials that do not meet this Warranty within the specified time periods. These remedies are exclusive.

D. Limitation of Liability

Except where prohibited by law, 3M SHALL NOT UNDER ANY CIRCUMSTANCES BE LIABLE TO PURCHASER OR USER FOR ANY DIRECT (EXCEPT FOR THE LIMITED REMEDY PROVIDED ABOVE), INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES (INCLUDING, BUT NOT LIMITED TO, LABOR, NON-3M MATERIAL CHARGES, LOSS OF PROFITS, REVENUE, BUSINESS, OPPORTUNITY, OR GOODWILL) RESULTING FROM OR IN ANY WAY RELATED TO SELLER'S PRODUCTS, SERVICES or THIS BULLETIN. This limitation of liability applies regardless of the legal or equitable theory under which such losses or damages are sought including breach of contract, breach of warranty, negligence, strict liability, or any other legal or equitable theory.

E. Additional Limitations

See the [3M Graphics Warranties Brochure](#) at 3Mgraphics.com, which gives the terms, additional limitations of the Warranty, if any, and limitations of liability.

F. 3M Performance Guarantee

Subject to Stipulations set forth in Section H, below

Graphics constructed with the 3M materials specified and in the exposure specified in the Warranty Period, Section F(1), are eligible for the 3M Performance Guarantee. This Warranty only covers the performance of the recommended 3M products used in the graphic construction when imaged with the printers and OEM inks listed in the most current version of the [3M Performance Guarantee Matrix](#) at 3Mgraphics.com. The Matrix may also list certain restrictions for using the film covered in this Bulletin. For warranties for other exposures, see Section H(1) on page 9.

Warranty Period for 3M Product Performance, in Years

(1) **Warranty Period**
for 3M Product Performance
in a Standard U.S. Vertical
Exposure

Film	Graphic Protection	Vehicles***	Outdoor & Indoor Signs	Watercraft	Inks & Printers**
IJ180 IJ180C IJ180Cv3	8518 8519 8520 8915	3	3	2	See the 3M Performance Guarantee Matrix
	8528* 8548G* 8549L*	4	3	2	
	1920DR	3	3	—	
	9740i	3	3	2	

* For information about overlaminates 8528, 8548G, and 8549L horizontal Warranty Period, please see Section H(2).

** Some of the graphic protection products and graphic types may not be approved for this film on certain printing platforms. Always refer to the Performance Guarantee Matrix.

*** Films 7710-LD and SGH6: may be applied over overlaminates only for vehicle wrap graphics and for use on selected high impact areas of the vehicle. Warranty Period remains the same as shown in the Performance Guarantee Matrix. See [3M Instruction Bulletin 5.47](#) for complete details.

G. 3M™ MCS™ Warranty

Subject to Stipulations set forth in Section H, below

Finished graphics constructed with the materials specified and the exposure specified in the Warranty Period tables, Section G(2), are eligible for the 3M™ MCS™ Warranty. For warranties for other exposures, see Section H(1) on page 9.

(1) **Certificate of 3M™ MCS™ Warranty Requirement**

Only graphics manufacturers having a current Certificate of 3M™ MCS™ Warranty are eligible to extend this Warranty to their customers.

(2) **Warranty Period**
for Finished Graphics
in a Standard U.S. Vertical
Exposure

See Section 4D on page 5 for complete definitions of these graphic types:
 VEH = Commercial Vehicle, Fleet Truck and Trailer, Bus, Personal Vehicles
 OUT = Outdoor Signs, OEM
 WATER = Watercraft Graphics
 IN = Indoor Signs

See *Warranty Period Matrices on the next page.*

Warranty Period for Finished Graphics, in Years

SOLVENT PRINTERS and INKS	EFI™ VUTEK® 150, 2360/3360, 3300/5300, 3000/5000 Printers				HP Scitex XL 1200, XL 1500 Printers				HP Scitex TJ8300 and TJ8350 Industrial Presses			
	3M Ink Series 1500v2				3M Ink Series 4400				3M Ink Series 4800			
Graphic Protection	VEH	OUT	WATER	IN	VEH	OUT	WATER	IN	VEH	OUT	WATER	IN
8518, 8519, 8520, 8915 ❖	7	4	2	8	7	4	2	8	7	4	2	8
8528 ■ ❖	7/3	4	2	8	7/3	4	2	8	7/3	4	2	8
8548G, 8549L ■ ❖	7/2	4	2	8	7/2	4	2	8	7/2	4	2	8
8908, 8909	—	1	—	3	—	1	—	3	—	1	—	3
1920DR	3	3	2	5	—	—	—	—	3	3	2	5
9740i	5	4	2	8	5	4	2	8	5	4	2	8
8530	2	2	—	3	2	2	—	3	2	2	—	3
none	—	2	—	2	—	2	—	3	—	2	—	3

SOLVENT PRINTERS and INKS	SIIT ColorPainter H Series H-74s, H-104s, H2-74s, H2-104s, W-54s & W-64s Printers				Seiko I Infotech ColorPainter™ M-64s Printers			
	GX 3M Ink Series				SIIT SX 3M Ink Series			
Graphic Protection	VEH	OUT	WATER	IN	VEH	OUT	WATER	OUT
8518, 8519, 8520, 8915 ● ❖	7	4	2	8	7	4	2	8
8528 ■ ❖	7/3	4	2	8	7/3	4	2	8
8548G, 8549L ■ ❖	7/2	4	2	8	7/2	4	2	8
8908, 8909	—	—	—	—	—	—	—	—
1920DR	3	3	2	5	3	3	2	5
9740i	5	4	2	8	—	—	—	—
8530	—	—	—	—	—	—	—	—
none	—	2	—	2	—	2	—	2

LATEX PRINTERS and INKS	HP Designjet L65500; Scitex LX600, LX800, LX820, LX850; Latex 820, 850 Printers				HP Designjet L65500; Scitex LX600, LX800, LX820, LX850; Latex 820, 850 Printers				HP Designjet L26100, L26500, L28500; Latex 210, 260, 280 Printers			
	HP 3M LX600 Latex Ink				HP LX610 Latex Ink a 3M™ MCS™ Warranty Component				HP 792 Latex Ink a 3M™ MCS™ Warranty Component			
Graphic Protection	VEH	OUT	WATER	IN	VEH	OUT	WATER	IN	VEH	OUT	WATER	IN
8518, 8519, 8520, 8915 ❖	5	4	2	7	5	4	2	7	5	4	2	7
8528, 8548G, 8549L ■ ❖	5/2	4	2	7	5/2	4	2	7	5/2	4	2	7
1920DR	2	2	—	3	2	2	—	3	2	2	—	3

LATEX PRINTERS and INKS	HP Latex 3000 Printer				HP Latex 360 Printer			
	HP 881 Latex Ink a 3M™ MCS™ Warranty Component				HP 831 Latex Ink a 3M™ MCS™ Warranty Component			
Graphic Protection	VEH	OUT	WATER	IN	VEH	OUT	WATER	IN
8518, 8519, 8520, 8915 ❖	5	3	2	5	5	3	2	5
8528, 8548G, 8549L ■ ❖	5/2	3	2	5	5/2	3	2	5
1920DR	2	2	—	3	2	2	—	3

■ Overlaminates 8528, 8548G, and 8549L: first number represents the vertical Warranty Period and the second number the horizontal Warranty Period on vehicle graphics. Please see Section H(2).

● Clear 8915 is not approved for or warranted for use with Seiko I Infotech's GX 3M Ink Series.

❖ Films 7710-LD and SGH6: may be applied over one of these overlaminates only for vehicle wrap graphics and for use on selected high impact areas of the vehicle. Warranty Period remains the same as shown in this table. See [3M Instruction Bulletin 5.47](#) for complete details.

Warranty Period for Finished Graphics, in Years

UV PRINTERS and INKS	EFI™ VUTEK® PV200 Printer				EFI™ VUTEK® GS3250LXr and GS5500LXr Pro Printers				EFI™ VUTEK® GS2000, GS3200, GS3250 & GS Pro Series Printers			
	3M Ink Series 2200UV				EFI™ VUTEK® GSLXr 3M Superflex UV Ink (excludes White Ink)				GS 3M™ Premium UV Inks			
Graphic Protection	VEH	OUT	WATER	IN	VEH	OUT	WATER	IN	VEH	OUT	WATER	IN
8518, 8519, 8520, 8915 ❖	7	4	2	8	7	3	2	5	7	4	2	8
8528 ■ ❖	7/3	4	2	8	7/2	3	2	5	7/3	4	2	8
8548G, 8549L ■ ❖	7/2	4	2	8	7/2	3	2	5	7/2	4	2	8
1920DR	—	—	—	—	—	—	—	—	3	2	—	5
9740i	5	4	2	8	5	2	2	5	5	3	2	8
none	—	3	—	3	—	—	—	—	—	2	—	3

UV PRINTERS and INKS	EFI™ VUTEK® QS2000, QS3200, QS3220, QS220 Printers				EFI™ R3225 UV Roll-to-Roll Printer				EFI™ VUTEK® GS5000r, GS3250r Printer			
	3M Ink Series 2800UV				R3225 3M™ UV Inks				GSr 3M™ Premium UV Inks			
Graphic Protection	VEH	OUT	WATER	IN	VEH	OUT	WATER	IN	VEH	OUT	WATER	IN
8518, 8519, 8520, 8915 ❖	7	4	2	8	5	4	2	8	7	4	2	8
8528 ■ ❖	7/3	4	2	8	5/3	4	2	8	7/3	4	2	8
8548G, 8549L ■ ❖	7/2	4	2	8	5/2	4	2	8	7/2	4	2	8
1920DR	—	—	—	—	3	2	—	5	3	2	—	5
9740i	5	4	2	8	5	3	2	8	5	3	2	8
none	—	3	—	3	—	2	—	3	—	2	—	3

UV PRINTERS and INKS	Mimaki UJV-160, JFX-1631 & 1615R Printers				Mimaki UJV500-160 Printer			
	Mimaki Ink Series LF-200 Manufactured by 3M				Mimaki UV Ink LUS-200 Manufactured by 3M			
Graphic Protection	VEH	OUT	WATER	IN	VEH	OUT	WATER	IN
8518, 8519, 8520, 8915 ❖	7	4	2	8	5	4	2	8
8528 ■ ❖	7/3	4	2	8	5/3	4	2	8
8548G, 8549L ■ ❖	7/2	4	2	8	5/2	4	2	8
1920DR	—	—	—	—	3	2	—	5
9740i	—	—	—	—	5	3	2	8

- Overlaminates 8528, 8548G, and 8549L: first number represents the vertical Warranty Period and the second number the horizontal Warranty Period on vehicle graphics. Please see Section H(1) on page 9.
- ❖ Films 7710-LD and SGH6: may be applied over one of these overlaminates only for vehicle wrap graphics and for use on selected high impact areas of the vehicle. Warranty Period remains the same as shown in this table. See [3M Instruction Bulletin 5.47](#) for complete details.

**(3) Paint Refurbishing
Reimbursement Remedy**

- a. **Paint Staining**
- b. **For Commercial and Recreational Vehicles**

See the General Warranty Stipulations, Section H(2)c on page 9.

This Policy applies to commercial vehicles (e.g., automobiles, vans, buses) and recreational vehicles only, and specifically does not include Personal Vehicles or Watercraft. Refer to [3M Instruction Bulletin 5.36](#) for complete details.

- A *Pre-Installation and Inspection Report* (in Instruction Bulletin 5.36) must be completed **prior to graphic installation** and submitted with any claim for paint damage sustained during the removal of 3M removable or changeable graphic film from vehicles.
- A separate report for each vehicle involved in a claim is required.

c. For Watercraft

This applies to Watercraft only and specifically does not include any other type of vehicle. Refer to [3M Instruction Bulletin 5.42](#) for complete details.

- A *Pre-Installation and Inspection Report* (in Instruction Bulletin 5.42) must be completed **prior to graphic installation** and submitted with any claim.
- A separate report for each watercraft involved in a claim is required.
- Graphics must be applied above the static water line.
- Graphics must be cut at seams and all edges and seams and edges must be sealed.

H. General Warranty Stipulations for 3M™ MCS™ Warranty and 3M Performance Guarantee

These stipulations apply to both the 3M™ MCS™ Warranty and 3M Performance Guarantee. General provisions for these stipulations are covered in the [3M Graphics Warranties Brochure](#) at 3Mgraphics.com.

(1) Reduced Warranty Period for Other Graphic Exposures

For other graphic exposures, multiply the Warranty Period (in years) for your graphic construction as shown in the applicable Warranty Period tables, Section G(2) on page 6 or Section F(1) on page 6, by the percentage shown for the intended graphic exposure. See page 5 for the graphic exposure definitions.

a. Reduced Warranty Period for Other Graphic Exposures with Most Graphic Protection Options

If the Graphic Exposure is:	Use this Percentage of U.S. Vertical Exposure, Warranty Period	Calculation Examples
U.S. Non-vertical	50% (0.5)	0.5 x 7 years = 3.5 years 0.5 x 4 years = 2.0 years
Desert Southwest Vertical	70% (0.7)	0.7 x 7 years = 4.9 years 0.7 x 4 years = 2.8 years
Desert Southwest Non-vertical	35% (0.35)	0.35 x 7 years = 2.45 years 0.35 x 4 years = 1.4 years
Horizontal	0%	0

b. Horizontal Warranty Period ONLY for Overlaminates 8528, 8548G, or 8549L

Printed film as specified in this Bulletin for vehicle graphics with the following overlamine:

3M™ MCS™ Warranty Period

Overlamine 8528 using solvent or UV inks: U.S. = 3 years; Desert S.W. = 2.1 years
Overlamine 8528 using latex inks, 8548G, or 8549L: U.S. = 2 years; Desert S.W. = 1.4 years

3M Performance Guarantee Warranty Period

Overlaminates 8528, 8548G, or 8549L: U.S. = 2 years; Desert S.W. = 1.4 years

(2) Removal Warranty with Heat or Chemicals

a. For the 3M™ MCS™ Warranty Only

Within the stated Warranty Period, if this film cannot be removed with heat and/or chemicals, or if more than 30% of the adhesive residue remains on the substrate, 3M will reimburse a reasonable portion of extra removal costs.

b. For the 3M Performance Guarantee

Within the stated Warranty Period, if this film cannot be removed with heat and/or chemicals, or if more than 30% of the adhesive residue remains on the substrate, 3M will reimburse a reasonable portion of 3M material cost.

c. Removal Warranty Exceptions

The following exceptions are not covered by the Removal Warranty.

- Substrate damage due to:
 - removing film from a pre-existing graphic.
 - removing film that was applied to painted wallboard or any unapproved substrate.
 - removing film from paint that is not firmly bonded to the substrate.

Continued on the next page.

- No guarantee is made for:
 - paint staining. 3M does not warrant vehicle paint staining that may be visible after removing an inkjet printed graphic with an overlamine. To reduce the risk of this problem, always remove the graphic by the end of the Warranty Period.
 - ease or speed of removal of any graphic.
 - removal from paint that is improperly cured.
 - removal from aged paint or metals, surface oxidation or chalking; user must test, approve and accept liability for such applications.
 - removal from horizontally-exposed outdoor applications (except graphics using overlaminates 8528, 8548G, or 8549L as described in this Bulletin).

(3) Abrasion and Loss of Gloss

Abrasion damage and loss of gloss are not covered by any 3M Warranty. This is considered normal wear and tear. However, to help maintain the appearance of your graphic, use the recommended graphic protection whenever:

- it is required for the construction and end use as shown in the Warranty Period tables.
- the graphic, **including printed vehicle or watercraft graphics**, is exposed to abrasive conditions, harsh cleaners or chemicals.

(4) Application Outside the U.S.

Contact the 3M organization for that country.

(5) Application to Glass

3M accepts no liability for glass breakage when using this film for window graphics. See [3M Instruction Bulletin 5.1](#) for details.

(6) Watercraft Warranty

This applies to Watercraft only and specifically does not include any other type of vehicle. Refer to [3M Instruction Bulletin 5.42](#) for complete details.

- A *Pre-Installation and Inspection Report* (in Instruction Bulletin 5.42) must be completed **prior to graphic installation** and submitted with any claim.
- A separate report for each watercraft involved in a claim is required.
- Graphics must be applied above the static water line.
- Graphics must be cut at seams and all edges and seams and edges must be sealed.

(7) Graphics Made Using Paint Protection Films

- Never laminate paint protection films 7710-LD or SGH6 to the vehicle wrap prior to installing it to the vehicle.
- A vehicle wrap will be eligible for any applicable 3M Warranty only if:
 - the third layer of film is paint protection film 7710-LD or SGH6 and
 - the paint protection film is not applied over an existing overlap, which could create more than three layers.
- The paint protection films 7710-LD and SGH6 cannot be removed from the vehicle wrap without risk of damaging the image on the wrap or pulling up the wrap.

(8) Graphics Made with Components Not Sold or Recommended by 3M

The **3M™ MCS™ Warranty** does not, under any circumstances, cover graphics made with inks, film, graphic protection and/or application tapes that are not sold or recommended by 3M.

The **3M Performance Guarantee** does not, under any circumstances, cover OEM inks, even those approved by 3M for this program, or any type of 3M product failure that results from their use.

The user is solely responsible for the graphic appearance, performance and durability of graphic constructions that include any non recommended or qualified products.

6. Factors that Affect Graphic Performance Life

The actual performance life of a graphic is affected by:

- the combination of graphics materials used.
- complete ink drying or curing.
- selection, condition and preparation of the substrate.
- surface texture.
- application methods.
- angle and direction of sun exposure.
- environmental conditions.
- cleaning or maintenance methods.

7. Graphics Manufacturing



CAUTION

Before using any equipment, always read the manufacturer's instructions for safe operation.

A. Inkjet Printing

Always read and follow the ink manufacturer's written instructions on usage.

(1) Total Ink Coverage

The maximum recommended total ink coverage for this film is:

- **270%** when printed with all approved 3M solvent inkjet inks.
- **280%** when printed with all approved 3M UV inkjet inks and latex ink.
- **250%** when printed on the Mimaki JV5 Series printer with HS ink series (3M Performance Guarantee).

Do not exceed the recommended total ink coverage for the ink series used on this film. Too high a total physical ink amount on the film results in media characteristic changes, incomplete drying, overlamine lifting, and/or poor graphic performance. For additional details about total ink coverage, refer to the Product & Instruction Bulletin for 3M inks or the [3M Performance Guarantee Matrix](#) for OEM inks.

(2) Completely Dry Graphics

Important Note!

Incomplete drying can result in graphic failure including curling, increased shrinkage and adhesion failure, which are not covered under any 3M Warranty.

Always build enough time into your process to ensure complete drying of the graphic. Poorly dried film may become soft and stretchy, and the adhesive may become too aggressive. This can cause difficulty when applying an overlamine, rolling or applying the graphic. See the ink's 3M Instruction Bulletin for more details.

B. Cutting

The following are common cutting methods for this film. See [3M Instruction Bulletin 4.1](#) for details.

(1) Methods

- Bandsawing
- Hot kiss cutting
- Hot and cold steel rule
- Drum-type electronic cutting
- Knifeless™ Tape, 3M recommends using this product with this film. See <http://knifelessstechsystems.com/Home.aspx> for details, including videos and ordering information.
- Flat-bed electronic cutting
- Guillotine
- Hand cut
- Cold and hot steel-rule die cutting

(2) Size of Cut Text

These values are based on upper case Helvetica medium type. Weeding can be more difficult with smaller text.

Minimum stroke width:	0.25 inch (6.35 mm)
Minimum height:	3.0 inch (76.2 mm)
Minimum radius for end of stripe:	0.125 inch (3.18 mm)

C. Graphic Protection

Graphic protection may improve the appearance, performance and durability of the graphic.

- Overlamines must be cold or hot roll applied. When overlaminating UV inkjet printed graphics, 3M recommends using hot roll lamination to help minimize a silvered graphic appearance caused by bubbles being trapped within the valleys of a graphic. See [3M Instruction Bulletin 4.22](#) for details.
- Clear 8530 must be applied with a liquid laminator.

D. Application Tapes

(1) When to Use Premasking Tape

- Use as an application aid to increase stiffness, and to prevent stretching and damage during application.
- Use when little or no liner is exposed.

(2) When to Use Prespacing Tape

- Hold cut and weeded letters or graphics in registration after removing the film liner.
- Protect cut graphic parts from scratching or damage during application.
- Use when large amounts of liner are exposed.

(3) How to Select a Tape

Determine whether you want to premask the graphic or prespace cut pieces of film such as letters. Then locate the graphic protection used on your graphic in the following table, and use the corresponding tape. See [3M Instruction Bulletin 4.3](#) for complete details.

EXAMPLE: To premask a film without printing and graphic protection, use premasking tape SCPM-3. To prespace a film with Comply adhesive that includes clear 1920DR, use prespacing tape SCPS-55.

Select the tape based on what is on top of the graphic

Tape	None	8519 8520 8915 8549L	8908 8909	8530	1920DR	9740i	8518 8528 8548G
Premasking SCPM-3	■	■	■	■	■	—	—
Prespacing SCPS-2 <i>IJ180</i>	■	■	■	—	■	—	—
Premasking SCPM-44X	—	—	—	—	—	■	—
Prespacing SCPS-55 <i>use for films with Comply adhesive</i> ♦	■	■	—	—	■	■	—
Prespacing SCPS-53X	—	—	—	—	—	■	—

— = The use of this application tape is not recommended in this construction.

♦ = Prespacing tape does not adhere to the exposed liner of film IJ180Cv3, but it does adhere to the top of the film. Therefore, prespacing tape may still be useful when applying large graphics—even large cut graphics—with some smaller cut and weeded graphics to hold the elements in alignment. Use film IJ180 or IJ180C for more intricately cut and weeded graphics.

8. Application and Installation

Install the film using the dry application method.

In addition to other Bulletins specified in this document, the following Bulletins provide details that you may need to successfully apply a graphic.

- Application, special applications and vehicles. [3M Instruction Bulletin 5.4](#).
- Application, general procedures for indoor and outdoor dry applications. [3M Instruction Bulletin 5.5](#).
- A guide to understanding and applying graphics to common indoor and outdoor wall surfaces. [3M Instruction Bulletin 5.37](#).
- 3M™ Vehicle Channel Applicator Tools. [3M Product & Instruction Bulletin V-Tools](#).

Continued on the next page.

When these films are printed with solvent-based inks and use overlamine 8518, 8519, 8520, 8528 or 8915, the graphics can be stretched up to 130% without using primer or making relief cuts. When using overlamine 8548G or 8549L, graphics can be stretched up to 150% (e.g., a 10 inch [25 cm] piece of film can stretch to 15 inches [39 cm]) without using primer or making relief cuts. When stretching at higher levels, primer and/or relief cuts are required. See [3M Instruction Bulletin 5.36](#) for complete details.

A. Pressure-activated Adhesive

- The pressure-activated adhesive on this film offers:
 - smooth sliding into position on a substrate;
 - fast finger tacking to check position; and
 - easy snap up and repositioning when you need it.
- The **snap up and reposition feature is lost:**
 - when firm pressure with a squeegee or other application tool is applied.
 - at application temperatures above 100°F (38°C) even if only light finger pressure was used for tacking.
 - if any part of the film is removed from the original liner and reapplied to the same or another liner.
 - solvent from inkjet ink has not completely dried or cured, which affects both slide-ability and snap up.

B. Working with Air Release Channels

Air release channels are a characteristic of films with Comply adhesive. Films designated as Cv3 offer the ultimate in invisible air release channels.

- The channels will be damaged and effective air removal affected if you remove and attempt to change liners or reapply the same liner.
- For the best results, always work from the center out to the edges of the graphic to allow trapped air to exit through the air release channels. If the channels are closed off by firm pressure and air is trapped, use an air release tool to aid in removing air bubbles. See [3M Instruction Bulletin 5.4](#) for details.

Video



Click here to see how 3M's Comply adhesive technology works.

C. 3M™ Tape Primer 94

Although this product does not require the use of primer 94 in the areas where the film will be stretched, it is always a good practice to use primer to maximize a graphic's bond to its substrate.

D. Graphics Printed with UV Inkjet Inks are Heat Sensitive!

UV inkjet inks may crack if too much heat is used during graphic application to complex curves and deep contours as well as around rivets. When using a heat gun or other heat source during application, make sure the film surface temperature does not exceed 212°F (100°C).

Using additional heat in the post-application process may also cause UV inkjet ink to crack.

For the best results, **always do a test application** of a UV printed graphic to determine how much heat can be used without damaging the image.

E. Application to Vehicles

Read and follow all instructions, and complete the *3M Automobiles, Vans and Buses Pre-installation Inspection Record* in [3M Instruction Bulletin 5.36](#), prior to manufacturing or applying any graphic to an automobile, van or bus.

F. Application to Watercraft

Read and follow all instructions, and complete the *3M Watercraft Graphics Pre-installation Inspection Record* in [3M Instruction Bulletin 5.42](#), before manufacturing or applying any graphic to a watercraft.

Graphics applied to watercraft require edge sealing. Refer to [3M Instruction Bulletin 5.42](#) for details.

G. Application to Other Substrates

Please refer to the 3M Bulletins mentioned in Section 8, on page 12.

H. Edge Sealing

Vehicle, indoor and outdoor graphics. These films may require edge sealing. Applications such as rail cars may benefit from using edge sealer 3950 or edge tape 8914 when subject to external sources such as abrasion and/or power-washing. Refer to [3M Product & Instruction Bulletin Edge Sealers](#) for details.

Watercraft graphics. Graphics applied to watercraft require edge sealing. Refer to [3M Instruction Bulletin 5.42](#) for details.

I. Paint Protection Films

Refer to [3M Instruction Bulletin 5.47](#) for complete application instructions.

- Apply paint protection film 7710-LD or SGH6 only after the laminated vehicle graphic is fully applied.
- Clean the applied vehicle graphic before applying the paint protection film.
- Wet apply the paint protection film.
- Keep the vehicle indoors and out of direct sunlight for 24 hours.
- After 24 hours, spray the top of the paint protection film with a wetting solution, squeegee all edges with an edge-protected squeegee and wipe dry.

9. Maintenance and Cleaning

Use a cleaner designed for high-quality painted surfaces. The cleaner must be wet, non-abrasive, without strong solvents, and have a pH value between 3 and 11 (neither strongly acidic nor strongly alkaline.) See [3M Instruction Bulletin 6.5](#).

10. Removal

Removal requires heat and/or chemicals. The ease and rate of removal depends on a number of factors. See [3M Instruction Bulletin 6.5](#) for details. A chemical remover system is available for graphics printed with solvent-based ink. Follow the procedures for using 3M™ Controltac™ Film Remover R-221 and Adhesive Remover R-231 and for additional removal details.

11. Shelf Life, Storage and Shipping

A. Shelf Life

Total shelf life: 3 years from the date of manufacture on the original box. If you do process the film, do so within 2 years and apply within 1 year. If you do not process the film, apply it within 3 years.

B. Storage Conditions

- 40° to 100°F (4° to 38°C)
- Out of sunlight
- Clean dry area
- Original container
- Bring the film to print room temperature before using

C. Shipping Finished Graphics

Flat, or rolled printed side out on 6 inch (15 cm) or larger core. This helps prevent the application tape, if used, from popping off.

12. Health and Safety



When handling any chemical products, read the manufacturers' container labels and the Safety Data Sheets (SDS) for important health, safety and environmental information. To obtain SDS sheets for 3M products go to 3M.com/MSDS, or by mail or in case of an emergency, call 1-800-364-3577 or 1-651-737-6501.

When using any equipment, always follow the manufacturers' instructions for safe operation.

13. Bulletin Change Summary

Modified and new content is marked with a black bar in the margin. Added 3M™ Envision™ Luster Wrap Overlaminates 8549L. Discontinued 3M Piezo Inkjet Ink Series 6200 for Agfa Jeti 3312, 3318, 3324 & 5024 [Gandinnovations] Printers and 3M Piezo Inkjet Ink Series 2700UV for Durst Rho 160R & 351R Printers. Added SIIT SX 3M Ink Series for Seiko Infotech ColorPainter™ M-64s Printer, HP 831 Latex Ink for HP Latex 360 Printer, and EFI™ VUTEK® GSLXr 3M Superflex UV Ink (*excludes White Ink*) for EFI™ VUTEK® GS3250LXr and GS5500LXr Pro Printers. Increased the Warranty Period from 5 to 7 years for UV printed finished graphics protected by a recommended film overlaminate and applied as a vertical, vehicle graphic. Added statement about Certificate of 3M™ MCS™ Warranty. Discontinued RG180 and FN180 (all versions) films. The 3M Related Literature section has been replaced by direct links to the most current versions of Bulletins or warranty information you may need to successfully use this product. All links are blue underlined text.



Commercial Solutions

3M Center, Building 220-12E-04
St. Paul, MN 55144 USA
General & Technical
1-800-328-3908
Fax 1-651-736-4233

www.3Mgraphics.com

3M Canada

PO Box 5757
London, Ontario
Canada N6A 4T1
General 1-800-265-1840
Fax 519-452-6245

3M México S.A. de C.V.

Av. Santa Fe No. 55
Col. Santa Fe, Del. Alvaro Obregón
México D.F. 01210
General 5255-5270-0400
Fax 5255-5270-2277

3M Puerto Rico, Inc.

350 Chardon Avenue
Suite 1100
San Juan, PR 00918
General 787-620-3000
Fax 787-620-3018

3M, Controltac, Comply, Envision, MCS, Scotchgard, Scotchcal and VenturShield are trademarks of 3M Company.

EFI is a trademark and VUTEK is a registered trademark of EFI Inc. ColorPainter is a trademark of Seiko Infotech. Knifeless is a trademark of Knifeless Technology Systems. All other trademarks are the property of their respective owners.

©3M 2014. All rights reserved.